

MM Kwidzyn sp. z o.o.

UL. LOTNICZA 1,

82-500 KWIDZYN, POLAND




KWIDZYN

TECHNICAL DATA SHEET

SPEED-E PREPRINT

Parameter	Standard	Unit	Measurement		
Substance	EN ISO 536	g/m ²	75* ± 2	80 ± 2	90 ± 2
Thickness	ISO 534	µm	100 ± 3	106 ± 3	116 ± 3
Moisture content	EN ISO 287	%	3,8 - 5,2	3,8 - 5,2	3,8 - 5,2
Whiteness	ISO 11475	CIE units	166 ± 2	166 ± 2	166 ± 2
Opacity	ISO 2471	%	93 +2/-1	94 +2/-1	95 +2/-1
Bendtsen roughness	ISO 8791-2	ml/min	180 ± 50	180 ± 50	180 ± 50
Cobb 60	EN ISO 535	g/m ²	≤30	≤30	≤30

* Subject to trim and accumulation. For more information contact your dedicated customer service team.



AVAILABLE CERTIFICATION:



✓ 100% ECF fibres