



1

## Technical specifications

Characteristics	Specification	Indication	Testing method
<b>Drainage</b>			
Freeness	350 ml (+/- 10 %)		ISO 5267/2
<b>Bauer McNett / Fibre length</b>			
Long fibre fraction > 30 mesh		37 %	
Medium fibre fraction 30-200 mesh		43 %	
Fines < 200 mesh		20 %	
Fibre length		1.3 mm	PulpEye
<b>Shives</b>			
Somerville		0.08 %	
<b>Sheet properties</b>			
Density	360 kg/m <sup>3</sup> (+/- 10 %)		ISO 534
Bulk	2.8 cm <sup>3</sup> /g (+/- 10 %)		ISO 534
Tensile index	26 Nm/g (+/- 10 %)		ISO 1924-2
Breaking length	2.7 km (min. 2.4 km)		ISO 1924-2
Tear index	5.6 mNm <sup>2</sup> /g (+/- 10 %)		ISO 1974
<b>Optical properties</b>			
Brightness	75 % (min. 73 %)		ISO 2470
Opacity	84 % (80.6 %–87.4 %)		ISO 2471
<b>Others</b>			
pH	8.1–9.1*		

2

## Testing method

## Tolerances

Testing climate	23 °C 50 %	+/- 1 °C +/- 2 % rH
Disintegration	10 minutes on 90 degrees water, 3000 rpm +/- 5 %	
Forming of handsheets	PFI sheetformer	
Optical physical testing of handsheets	In accordance to ISO standards	
Values measured at time of production	*pH value can be reduced to 7 on request	

3

## Mill certificates

Forest management	FSC® DNC-COC-000756, DNC-CW 000756 and PEFC™ 143468-2013-CoC-NOR-NA
Environmental management	ISO 14001
Quality management	ISO 9001
Energy management	ISO 50001